
**Internal combustion engines — Piston
rings —**

**Part 5:
Quality requirements**

*Moteurs à combustion interne — Segments de piston —
Partie 5: Exigences de qualité*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 6621-5:2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Visible defects	2
5 Material	12
6 Raised material caused by marking of rings	13
7 Machining of periphery and sides — unintentional deviation from ideal profile and flatness	13
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6621-5 was prepared by Technical Committee ISO/TC 22, *Road vehicles*.

This second edition cancels and replaces the first edition (ISO 6621-5:1988), which has been technically revised.

ISO 6621 consists of the following parts, under the general title *Internal combustion engines — Piston rings*:

- *Part 1: Vocabulary*
- *Part 2: Inspection measuring principles*
- *Part 3: Material specifications*
- *Part 4: General specifications*
- *Part 5: Quality requirements*

Introduction

ISO 6621 is one of a number of series of International Standards dealing with piston rings for reciprocating internal combustion engines. Others are ISO 6621 ^[1], ISO 6622, ISO 6623, ISO 6624, ISO 6625, ISO 6626 and ISO 6627 (see Bibliography for details).

The common features and dimensional tables presented in this part of ISO 6621 constitute a broad range of variables, and the designer, in selecting a particular ring type, should bear in mind the conditions under which it will be required to operate. The designer also refers to the specifications and requirements of ISO 6621-3 and ISO 6621-4 before completing his selection.

The difficulty of trying to define in absolute terms the quality attainable in normal commercial manufacture of piston rings is well known. In this part of ISO 6621, the commonly encountered aspects of quality in terms of casting defects and other departures from ideal are quantified. Many minor defects are clearly quite acceptable; other defects because of size or number are inadmissible.

STANDARDSISO.COM : Click to view the full PDF of ISO 6621-5:2005

Internal combustion engines — Piston rings —

Part 5: Quality requirements

1 Scope

This part of ISO 6621 specifies those quality aspects that are capable of definition but not normally found on a drawing specification.

It covers the following:

- single-piece piston rings of grey cast iron or steel;
- multi-piece piston rings (oil control rings) consisting of cast iron parts and spring components;
- single-piece and multi-piece oil control rings of steel, i.e. oil control rings in the form of strip steel components or steel segments (rails) with spring expander components.

In addition to specifying certain of the limits of acceptance relating to inspection measuring principles (covered by ISO 6621-2), this part of ISO 6621 also covers those features for which no recognized quantitative measurement procedures exist and which are only checked visually with normal eyesight (spectacles if worn normally) and without magnification. Such features (superficial defects) are additional to the standard tolerances of ring width, radial wall thickness and closed gap.

This part of ISO 6621 does not establish acceptable quality levels (AQL), it being left to manufacturer and client to decide the appropriate levels jointly. In this case, the recommendations of ISO 2859 are followed.

This part of ISO 6621 specifies the quality requirements of piston rings for both reciprocating internal combustion engines and compressors working under analogous conditions. It is applicable to all such rings of a diameter ≤ 200 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6621-1, *Internal combustion engines — Piston rings — Part 1: Vocabulary*

ISO 6621-3, *Internal combustion engines — Piston rings — Part 3: Material specifications*

ISO 6621-4, *Internal combustion engines — Piston rings — Part 4: General specifications*

ISO 6622-1, *Internal combustion engines — Piston rings — Part 1: Rectangular rings made of cast iron*

ISO 6622-2, *Internal combustion engines — Piston rings — Part 2: Rectangular rings made of steel*

ISO 6623, *Internal combustion engines — Piston rings — Scraper rings made of cast iron*

ISO 6624-1, *Internal combustion engines — Piston rings — Part 1: Keystone rings made of cast iron*

ISO 6624-2, *Internal combustion engines — Piston rings — Part 2: Half keystone rings made of cast iron*

ISO 6624-3, *Internal combustion engines — Piston rings — Part 3: Keystone rings made of steel*

ISO 6624-4, *Internal combustion engines — Piston rings — Part 4: Half keystone rings made of steel*

ISO 6625, *Internal combustion engines — Piston rings — Oil control rings*

ISO 6626, *Internal combustion engines — Piston rings — Coil-spring-loaded oil control rings*

ISO 6626-2, *Internal combustion engines — Piston rings — Part 2: Coil-spring-loaded oil control rings of narrow width made of cast iron*

ISO 6627, *Internal combustion engine — Piston rings — Expander/segment oil control rings*

3 Terms and definitions

The terminology used in this part of ISO 6621 is as given in ISO 6621-1.

4 Visible defects

4.1 General

Visible defects are divided into two principle classes as described in 4.2 to 4.5.

The first class covers those defects frequently found in castings and includes such defects as porosity, sand inclusions, cavities, etc.

The second class of defect covers mechanical abrasions which may occur during forming, machining or handling of the rings, and includes scratches, dents, chipping, burrs and cracks.

Inspection of piston rings for such defects is generally carried out visually, without magnification, by inspectors having normal eyesight, corrected if necessary.

It is not intended that every ring be rigorously inspected for size and distribution of defects, but rather that the values given in the tables and text be used as a general guide. However, in case of doubt, the values given should be used as the means of judging the quality of the rings.

4.2 Pores, cavities and sand inclusions

Such defects are permissible on uncoated surfaces and edges provided that the values given in Table 1 for size, number and spacing are not exceeded.

Table 1 — Permissible values of size, number and spacing of pores, cavities and sand inclusions

Dimensions in millimetres

Nominal diameter d_1	Defect size max.				Number of defects per ring max.	Spacing of defects ^c min.
	on peripheral surface ^a	on other surfaces ^a	on peripheral edges	on other edges ^b		
$30 \leq d_1 < 60$	0,1	0,3	0,1	0,1	2	4
$60 \leq d_1 < 100$	0,15	0,5	0,1	0,2	4	4
$100 \leq d_1 < 150$	0,2	0,5	0,1	0,3	6	8
$150 \leq d_1 \leq 200$	0,2	0,8	0,1	0,4	8	8
^a The defects should not be closer to an edge than one-half of the maximum permissible size of the defect, with a minimum of 0,2. ^b Does not apply to inside gap edges of piston rings with internal notch. ^c Spacing includes defects on adjacent or opposite surfaces.						

4.3 Scratches, indentations, depressions and cracks

4.3.1 Scratches

Isolated scratches are permissible provided that:

- no burrs are produced exceeding the permissible values given in 4.4.1.1;
- on turned peripheral surfaces, they are not deeper than the tool marks;
- on non-turned peripheral surfaces, they are not deeper than 0,004 mm;
- on the side faces, they are not deeper than 0,01 mm;
- on other surfaces, they are not deeper than 0,06 mm.

4.3.2 Indentations, depressions

Indentations and depressions are permissible provided that:

- the values given in Table 1 for number and spacing of defects are met;
- no burrs are produced exceeding the permissible values given in 4.4.1.1;
- they do not exceed the values for size and depth given in Table 2.

Rings of a plated/coated/nitrided type shall not have indentations or depressions on the periphery.

NOTE Indentations arising from hardness measurements on the side faces are acceptable provided that they do not exceed the limits given in Tables 2 and 11.

4.3.3 Cracks

No cracks are permissible.

See also 4.5.4 for chromium-plated peripheral surfaces and 4.5.6 for nitrided surfaces.

Table 2 — Permissible size of indentations and depressions

Dimensions in millimetres

Nominal diameter d_1	Defect size max.		Depth max.
	On peripheral surface	On side face	
$30 \leq d_1 < 100$	0,3	0,6	10 % of corresponding max. defect size
$100 \leq d_1 \leq 200$	0,5	1	

4.4 Edges

4.4.1 Edge configuration

All edges of the piston ring shall be sharp; ideally, they should be free from burrs and from ragged edges, whether arising from crumbling of material or from deburring. Such conditions are almost impossible to achieve regularly in volume production and hence both burrs and removal of edge material is permitted up to the maximum sizes given in 4.4.1.1 and 4.4.1.2.

4.4.1.1 Burrs

Burrs are permitted up to the maximum values given in Table 3. The orientation and direction of burrs shall relate to the functional surfaces of the piston ring; any burr present should point in the direction of sliding motion of the ring and not normal to the direction of sliding.

Any burrs remaining on the edges of rings should be firmly attached, forming an integral part of the edge.

Table 3 — Permissible size of burrs for all sizes of ring

Dimensions in millimetres

Burrs on edges adjacent to:	Cast iron & steel single & 2 piece rings	Maximum size of burr		
		Expander/segment oil control rings		
		Expander	Plated segment	Nitrided segment
Peripheral surface	0,006	0,01	0,004	0,004
Side faces	0,006	0,01	0,02	0,01
Butt ends (gap surface)	0,04	0,1	0,1	0,04
The outside groove face (oil rings)	0,2	—	—	—
The inside surface and the ends of the slots (oil rings)	0,5	0,5	0,1	0,1
All other surfaces	0,1	0,1	0,1	0,1

4.4.1.2 Edge material removal

To eliminate protruding burrs in any direction, it is permissible to remove material from the edges to the values given in Table 4.

Table 4 — Edge material removal in deburr operations

Dimensions in millimetres

Location of edge	Removal of material max.
On peripheral edges	0,08
On peripheral edges of the gap ^a	0,15
On inside edges of the gap	0,5 in circumferential direction
	0,25 in radial direction
On other edges	0,25
^a Does not apply to rings which have specified gap edge chamfers.	

4.4.2 Chipping and similar defects on peripheral edges, peripheral edges at the gap, outside gap corners and on peripheral chamfers

Chipping and similar defects are permitted at these points provided that:

- they are free of loosely adhering particles;
- no burrs are produced exceeding the values permitted in 4.4.1.1;
- they do not exceed half the width of any witness land on, for example, taper-faced rings;
- they do not exceed the values given in the following tables:
 - Table 5 for plain rings;
 - Table 6 for chromium plated or nitrided rings;
 - Table 7 for spray coated rings;
 - Table 8 for chamfers on all rings.

Typical defects are illustrated in Figures 1 to 6.

K_1 , K_2 , K_3 are always the dimensions of the defect measured along the edge cut by the defect.

F_1 , F_2 , F_3 are always the dimensions of the defect measured from normal to the edge cut by the defect.

However, when chipping or other defects occur on outside gap corners, i.e. when the defect crosses the intersecting edges of the peripheral edge and the peripheral edge of the gap, a convention is required.

The defect is taken as appropriate to the edge that contains the larger amount of the defect. For example, in Figure 3, most of the left side defect is on the peripheral edge and therefore the defect is appropriate to that edge. Hence, the K value lies along the peripheral edge and is denoted K_3 while the F value, although it lies along the peripheral edge of the gap, is taken as the dimension, measured normal to the peripheral edge and is denoted F_3 .

In the case of the defect on the right side corner, most of the defect lies along the peripheral edge of the gap and the defect is therefore appropriate to this edge. The measurement K_3 in this case is therefore measured along the peripheral edge of the gap and F_3 is its dimension normal to the edge of the gap.

The limitations for chipping and similar defects on peripheral edges, peripheral edges of the gap and opposite gap corners are given in 4.4.2.1 to 4.4.2.3.

4.4.2.1 Peripheral edges

Defects to be included in the assessment of the peripheral edge are all values of F_2 and K_2 as well as the F_3 , K_3 values of outside gap corner defects if these are appropriate to the peripheral edges, e.g. the left hand defect illustrated in Figure 3.

Maximum sizes are given in Tables 5, 6 and 7 (peripheral edge column).

4.4.2.2 Peripheral edges of the gap

Defects to be included in the assessment of the peripheral edges of the gap are all values of F_1 and K_1 as well as the F_3 , K_3 values of outside gap corner defects, if these are appropriate to the peripheral edges of the gap, e.g. the right hand defect illustrated in Figure 3.

Maximum sizes are given in Tables 5, 6 and 7 (peripheral edge of gap column).

However, an additional limitation is that the sum of the defect sizes measured in the axial direction, i.e. along the peripheral edge of the gap, shall not exceed the values given in Tables 5, 6 and 7.

The defects to be added taken from the examples in Figure 4 are K_3 (right hand corner) + $K_1 + F_3$ (left hand corner).

4.4.2.3 Opposite gap corners

Defects at outside gap corners are accounted for in the assessments shown in 4.4.2.1 and 4.4.2.2 either as peripheral edge defects or as peripheral edge of the gap defects.

However an additional limitation is that the sum of the defects measured circumferentially on opposite corners shall not exceed the values given in Tables 5, 6 and 7.

The defects to be added in Figure 5 are the K_3 value of the left hand corner plus the K_3 value on the opposite corner and the F_3 value of the right hand corner plus the K_3 value of the opposite corner.

Table 5 — Permissible size of chipping and defects on plain rings on peripheral edges, peripheral edges of the gap and outside gap corners

Dimensions in millimetres

Ring width h_1	Land width h_5	Defect in direction normal to the peripheral surface ^{ab}		Defect in direction along edge ^{ab}	
		on peripheral edge of gap	on peripheral edge	on peripheral edge of gap ^c	on peripheral edge
		F_1, F_3 max.	F_2, F_3 max.	K_1, K_3 max.	K_2, K_3 max.
$h_1 < 1,5$	—	0,15		0,4	
$1,5 \leq h_1 < 2$	—	0,2		0,5	
$2 \leq h_1 < 4$	—	0,3		0,6	
$4 \leq h_1 \leq 6$	—	0,3		0,6	
—	< 0,5	0,1		0,1	0,2
—	≥ 0,5	0,2		0,2	0,2

^a Number and spacing of defects to be in accordance with Table 1.


^b See Figures 1, 2, 3, 4 and 5.

^c Subject to a maximum of one-third of peripheral width of ring or land.

Table 6 — Permissible size of chipping and defects on rings with a chromium plated or nitrided peripheral surface, on the peripheral edges, peripheral edges of the gap and the outside gap corners

Dimensions in millimetres

Ring width h_1	Land width h_5	Defect in direction normal to the peripheral surface ^{ab}		Defect in direction along edge ^{ab}	
		on peripheral edge of gap	on peripheral edge	on peripheral edge of gap ^c	on peripheral edge
		F_1, F_3 max.	F_2, F_3 max.	K_1, K_3 max.	K_2, K_3 max.
$h_1 < 2$	—	0,2		0,3	
$2 \leq h_1 < 4$	—	0,2		0,4	
$4 \leq h_1 \leq 6$	—	0,3		0,4	
—	$< 0,5$	0,1	0,1	0,1	0,2
—	$\geq 0,5$	0,2	0,1	0,2	0,2
^a Number and spacing of defects shall be in accordance with Table 1. ^b See Figures 1, 2, 3, 4 and 5. ^c Subject to a maximum of one-third of peripheral width of ring or land.					




Key

K_1 dimension of the defect measured along the edge cut by the defect

F_1 dimension of the defect measured from normal to the edge cut by the defect

Figure 1 — Chipping on peripheral edges of the gap




Key

K_2 dimension of the defect measured along the edge cut by the defect

F_2 dimension of the defect measured from normal to the edge cut by the defect

Figure 2 — Chipping on peripheral edges




Key

K_3 dimension of the defect measured along the edge cut by the defect

F_3 dimension of the defect measured from normal to the edge cut by the defect


Figure 3 — Chipping on outside gap corners

**Key**

K_1, K_3 dimensions of the defect measured along the edge cut by the defect

F_3 dimension of the defect measured from normal to the edge cut by the defect


Figure 4 — Combination of Figures 1 and 3

**Key**

K_3 dimensions of the defect measured along the edge cut by the defect

F_3 dimension of the defect measured from normal to the edge cut by the defect

Figure 5 — Chipping on opposite gap corners

**Key**

L_1, L_2 dimensions of the defects

Figure 6 — Chipping on chambers

**Table 7 — Permissible size of chipping and defects on spray coated rings on peripheral edges
peripheral edges of the gap and outside gap corners**

Dimensions in millimetres

Ring width	Defect in direction normal to the peripheral surface ^{ab}		Defect in direction along edge ^{ab}	
h_1	on peripheral edges of the gap F_1, F_3 max.	on peripheral edges ^c F_2, F_3 max.	on peripheral edge of the gap ^d K_1, K_3 max.	on peripheral edge ^c K_2, K_3 max.
$h_1 < 2$	0,3		0,5	
$2 \leq h_1 < 4$	0,3		0,6	
$4 \leq h_1 \leq 6$	0,4		0,8	
^a Number and spacing of defects to be in accordance with Table 1.				
^b See Figures 1, 2, 3, 4 and 5.				
^c Only for fully faced and semi-inlaid design.				
^d Subject to a maximum of one-third of peripheral width of ring or coating.				

4.4.2.4 Chamfers at peripheral edges and peripheral edges at the gap

The limitations for chipping and similar defects on the chamfers at the peripheral edge and at the peripheral edge of the gap are as follows.

This type of defect is illustrated in Figure 6 and is more likely to occur on chromium plated chamfers (machined or un-machined), on machined chamfers on sprayed rings (fully coated), and on machined chamfers on grey iron rings. The maximum values of the defects allowable are given in Table 8 and are the same for all rings with chamfers on peripheral edge and peripheral edge of the gap.

Defects counted as on the chamfers shall not cut peripheral edges or peripheral edges of the gap but may just cut side faces or gap faces.

**Table 8 — Permissible size of chipping and defects on chamfers at the
peripheral edge and peripheral edge of the gap**

Dimensions in millimetres

Ring width h_1	Size of defect L_1, L_2 ^a max.
$h_1 < 2$	0,5
$2 \leq h_1 < 4$	0,8
$4 \leq h_1 \leq 6$	1,2
^a Number and spacing of defects to be in accordance with Table 1.	

4.4.3 Chipping and defects on inner edges and other edges

Chipping and defects on inner edges and other edges are permissible, on non-nitrided rings provided that:

- no burrs are produced exceeding the values given in 4.4.1.1;
- they do not exceed the maximum established values given in Table 1 for pores, cavities and sand inclusions.

4.4.4 Chipping and defects on inside gap corners

Chipping and defects on inside gap corners are permitted provided that:

- no burrs are produced exceeding the values given in 4.4.1.1;
- the rings do not have an internal notch;
- they do not exceed 0,3 mm in the radial direction and 0,5 mm in the circumferential and axial directions for coil spring-loaded oil control rings;
- they do not exceed the values given in Table 9 for remaining ring designs.

Table 9 — Permissible size of chipping and defects on inside gap corners

Dimensions in millimetres

Nominal diameter d_1	Size of defect measured		
	axially ^a	max. radially ^a	circumferentially
$30 \leq d_1 < 100$	0,6	0,8	1
$100 \leq d_1 \leq 200$	0,8	1	1,5
^a Subject to a maximum of one-third of the ring width or radial wall thickness.			

4.5 Other characteristics subject to visual inspection only

4.5.1 Discolouring or staining of surface

Discolouring or staining spread evenly or unevenly over the ring surfaces is permissible. (This does not include rust.)

4.5.2 Casting skin and deposits on inside surface

The following defects are permitted:

- unmachined (i.e. not cleaned up) areas within 5° of the gap ends;
- firmly adherent deposits arising from processing of the ring.

4.5.3 Chipping on uncoated surfaces

This is permissible provided the chip sizes do not exceed the maximum values established in Table 1 for pores, cavities and sand inclusions.

4.5.4 Chromium plated peripheral surface

The chromium plating shall be fully coherent, i.e. there shall be no visible macro-cracks, pores, blisters, chromium beads (undercut bulge in the surface) or pin holes.

Exceptions with regard to pinholes may be agreed upon between manufacturer and client.