

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION R 1403

GENERAL PURPOSE RUBBER WATER HOSE

1st EDITION

August 1970

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1403:1970

BRIEF HISTORY

The ISO Recommendation R 1403, *General purpose rubber water hose*, was drawn up by Technical Committee ISO /TC 45, *Rubber*, the Secretariat of which is held by the British Standards Institution (BSI).

Work on this question led to the adoption of Draft ISO Recommendation No. 1403, which was circulated to all the ISO Member Bodies for enquiry in December 1967. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Austria	Iran	Sweden
Brazil	Israel	Switzerland
Czechoslovakia	Italy	U.A.R.
France	Japan	United Kingdom
Germany	Netherlands	U.S.S.R.
Greece	New Zealand	Yugoslavia
Hungary	Poland	
India	Spain	

The following Member Bodies opposed the approval of the Draft :

Ireland
U.S.A.

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1403:1970

ISO Recommendation

R 1403

August 1970

GENERAL PURPOSE RUBBER WATER HOSE

INTRODUCTION

This ISO Recommendation has been prepared to provide minimum acceptable requirements for the satisfactory performance of rubber water hose for general purposes.

The list of nominal bores given in Table 1 (based on the R 10 series of preferred numbers) is not intended to be restrictive and will not preclude the manufacture of sizes outside this list which may be the subject of individual national standards.

1. SCOPE

This ISO Recommendation specifies the requirements for three types of general purpose rubber water hose as follows :

Type 1 – Low pressure : designed for a maximum working pressure of 0.6 MN/m^2 and a test pressure of 0.75 MN/m^2 (all sizes).

Type 2 – Medium pressure : designed for a maximum working pressure of 1.0 MN/m^2 and a test pressure of 1.6 MN/m^2 (sizes up to 50 mm nominal bore).

Type 3 – High pressure : designed for a maximum working pressure of 2.5 MN/m^2 and a test pressure of 5.0 MN/m^2 (sizes up to 25 mm nominal bore).

2. MATERIALS

The hose should be made with a rubber lining and have a reinforcement of natural or synthetic fibres and a rubber cover.

3. CONSTRUCTION

- 3.1 The lining and cover should be of uniform thickness, be reasonably concentric, and free from air holes, porosity and other defects.
- 3.2 The lining should be as smooth in the bore as is consistent with good manufacturing practice.
- 3.3 The cover of the moulded type hose should be smooth or fluted as required. The cover of mandrel built hose should have a smooth, fluted or cloth wrapped finish.
- 3.4 The hose should be uniformly vulcanized.

4. DIMENSIONS AND TOLERANCES

4.1 Bore

The bore of the hose should be in accordance with the nominal dimensions and tolerances given in Table 1.

TABLE 1 -- Nominal bores

Dimensions in millimetres			
Nominal bore	Tolerance	Nominal bore	Tolerance
10	± 0.75	40	± 1.50
12.5	± 0.75	50	± 1.50
16	± 0.75	63	± 1.50
20	± 0.75	80	± 2.00
25	± 1.25	100	± 2.00
31.5	± 1.25		

NOTE. — If special cases call for extra sizes :

- (a) for smaller or larger dimensions further numbers should be chosen from the R 10 series of preferred numbers with tolerances as given in ISO Recommendation R 1307, *Rubber hose — Bore sizes, test pressures and tolerances on length*.
- (b) for intermediate dimensions, numbers should be chosen from the R 20 series of preferred numbers, with the tolerances as for the next larger bore size from the R 20 series.

4.2 Length

The tolerances on cut lengths of hose should be as given in Table 2.

TABLE 2 — Tolerances on cut lengths

Dimensions in millimetres	
Length	Tolerance
up to 300	± 3.0
over 300 to 600	± 4.5
over 600 to 900	± 6.0
over 900 to 1200	± 9.0
over 1200 to 1800	± 12.0
over 1800	$\pm 1 \%$