



AEROSPACE MATERIAL SPECIFICATION

AMS2431™/3**REV. F**Issued 1998-04
Revised 2024-07

Superseding AMS2431/3E

Peening Media
Conditioned Carbon Steel Cut Wire Shot, Regular Hardness (45 to 52 HRC) (AWCR)

RATIONALE

AMS2431/3F results from a Five-Year Review and update of this specification with changes to Purpose (see 1.1); Tables 3, 4, and 5; Size (see 3.8.1.2); Composition (see 4.1.1); and Packaging and Identification (see 5.1.1).

1. SCOPE

1.1 Purpose

This specification, in conjunction with the general requirements for peening media covered in AMS2431, establishes the requirements for the procurement of conditioned carbon steel cut wire shot with a hardness of 45 to 52 HRC.

1.2 Application

Conditioned carbon steel cut wire shot, regular hardness, conforming to this specification is intended for use in peening metal surfaces to impart compressive stresses to these surfaces thereby increasing resistance to fatigue and stress-corrosion cracking. Generally, regular hardness conditioned carbon steel cut wire shot is used on parts of hardness less than 50 HRC.

2. APPLICABLE DOCUMENTS

Shall be in accordance with AMS2431.

3. TECHNICAL REQUIREMENTS

3.1 Conditioned carbon steel cut wire shot, regular hardness, shall conform to AMS2431 and the requirements specified herein.

3.2 Composition

Composition shall conform to the percentages by weight for carbon steel shown in Table 1, determined in accordance with ASTM E415 and ASTM E1019.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS2431/3F>

Table 1 - Composition

Element	Min	Max
Carbon	0.45	0.85
Manganese	0.30	1.30
Silicon	0.15	0.35
Phosphorus	--	0.040
Sulfur	--	0.050

3.3 Hardness

Not less than 90% of the readings shall fall within the range of 45 to 52 HRC, or equivalent, determined in accordance with ASTM E384 using a 500 g minimum load. Hardness testing shall be performed after the shot has been conditioned for shape.

3.4 Media Condition

Conditioned cut wire shot shall be free of shear cracks and burrs.

3.5 Contamination

Shot shall be clean and free of dirt, grit, oil, or grease.

3.6 Quality Requirements

Shot shall conform to 3.6.1 determined in accordance with 3.8.2.

3.6.1 Shape shall be predominantly spherical as a result of conditioning or rounding.

3.6.1.1 Acceptable Shapes

Shapes conforming to Figure 1 shall be in accordance with Table 2.

3.6.1.2 Marginal Shapes

Shapes conforming to Figure 2 are permissible to the extent specified in Table 2.

3.6.1.3 Unacceptable Shapes

Shapes conforming to Figure 3 are permissible to the extent specified in Table 2.

Table 2 - Shape requirements

Shot Size	Area per Field Square Inches (mm ²)	Number of Fields Viewed	Number of Marginal Particles All Fields Max ⁽¹⁾	Number of Unacceptable Particles All Fields Max ⁽²⁾
AWCR 116	1 (645)	3	7	2
AWCR 96	1 (645)	2	7	2
AWCR 80	1 (645)	2	10	3
AWCR 62	1 (645)	9	63	2
AWCR 54	1 (645)	7	66	2
AWCR 47	1 (645)	5	68	2
AWCR 41	1 (645)	4	70	2
AWCR 35	0.25 (161)	14	67	2
AWCR 32	0.25 (161)	12	60	2
AWCR 28	0.25 (161)	7	67	2
AWCR 23	0.25 (161)	5	70	2
AWCR 20	0.25 (161)	4	76	2
AWCR 17	0.0625 (40)	11	70	2
AWCR 14	0.0625 (40)	6	60	2
AWCR 12	0.0625 (40)	5	68	2
AWCR 7	0.0625 (40)	2	82	2

⁽¹⁾ Maximum number of marginal shapes is approximately 3% of the total number of particles viewed.

⁽²⁾ Maximum number of unacceptable shapes is approximately 1% of the total number of particles viewed.

3.6.2 Conditioning shall be accomplished by impacting the as-cut wire cylinders against a hardened target until a predominantly spherical shape (see Figure 1) has been obtained.

3.7 Size

Size shall conform to the requirements of Table 3, 4, or 5 as determined in accordance with 3.8.1.

Table 3 - Size requirements, 50-piece sample

Shot Size	Wire Diameter Inches	Wire Diameter Millimeters	Weight of 50 Pieces Grams
AWCR 116	0.116 ± 0.002	2.946 ± 0.05	5.77 to 7.05
AWCR 96	0.096 ± 0.002	2.438 ± 0.05	3.45 to 4.25
AWCR 80	0.080 ± 0.002	2.032 ± 0.05	2.09 to 2.55
AWCR 62	0.0625 ± 0.002	1.588 ± 0.05	0.98 to 1.20
AWCR 54	0.054 ± 0.002	1.37 ± 0.05	0.65 to 0.79
AWCR 47	0.047 ± 0.002	1.19 ± 0.05	0.43 to 0.52
AWCR 41	0.041 ± 0.002	1.04 ± 0.05	0.28 to 0.35
AWCR 35	0.035 ± 0.001	0.89 ± 0.025	0.18 to 0.22
AWCR 32	0.032 ± 0.001	0.81 ± 0.025	0.12 to 0.16
AWCR 28	0.028 ± 0.001	0.71 ± 0.025	0.09 to 0.11
AWCR 23	0.023 ± 0.001	0.58 ± 0.025	0.045 to 0.060
AWCR 20	0.020 ± 0.001	0.51 ± 0.025	0.035 to 0.045

Table 4 - Size requirements, 100-piece sample

Shot Size	Wire Diameter Inches	Wire Diameter Millimeters	Weight of 100 Pieces Grams
AWCR 17	0.017 ± 0.001	0.43 ± 0.025	0.040 to 0.055
AWCR 14	0.014 ± 0.001	0.36 ± 0.025	0.015 to 0.030
AWCR 12	0.012 ± 0.001	0.30 ± 0.025	0.010 to 0.020

Table 5 - Size requirements, 200-piece sample

Shot Size	Wire Diameter Inches	Wire Diameter Millimeters	Weight of 200 Pieces Grams
AWCR 7	0.007 ± 0.0005	0.177 ± 0.0125	0.0047 to 0.0078

3.8 Test Methods and Procedures

3.8.1 Size

3.8.1.1 The size of shot shall be determined by comparing a wire with a diameter as specified in Tables 3, 4, and 5 with the shot.

3.8.1.2 Fifty pieces of the conditioned media shall meet the weight requirements as shown in Table 3. One hundred pieces of the conditioned media shall meet the weight requirements of Table 4. Two hundred pieces of the conditioned media shall meet the weight requirements of Table 5.

3.8.2 Shape

Visual examination, at a minimum of 10X magnification for sizes AWCR 23 and larger and at a minimum of 30X magnification for sizes finer than AWCR 23, shall be performed using the areas of field and number of fields specified in Table 2 for each respective shot size.

4. QUALITY ASSURANCE PROVISIONS

Shall be in accordance with AMS2431 and the following:

4.1 Sampling and Testing for Composition, Hardness, Size, and Shape

Two samples of approximately 800 g each shall be selected from separate containers chosen at random from each lot. Each sample shall be split into test quantities as follows:

4.1.1 Composition

Each of the two samples shall be evaluated.

4.1.2 Hardness

Not less than 20 microhardness readings shall be made from each sample with no more than one impression on any one shot.

4.1.2.1 Samples for microhardness testing shall be prepared by encapsulating a representative amount of shot from each sample in a plastic mount and polishing down to nominal half spheres.

4.1.3 Size

Not less than 100 g from each sample shall be used for size evaluation.

4.1.3.1 Alternative methods for size evaluation may be used provided that they can be correlated to the weight method in 3.8.1.2 and are acceptable to the cognizant engineering organization.

4.1.4 Shape

Each sample shall consist of shot, in one layer, which completely fills the areas specified in Table 2. The number of fields viewed at magnification for each shot size shall be as indicated in Table 2.