

AEROSPACE MATERIAL SPECIFICATION



AMS3626

REV. G

Issued 1946-11
Revised 1993-01
Reaffirmed 1998-08
Stabilized 2011-11

Superseding AMS3626F

Plastic Moldings and Extrusions, Methyl Methacrylate

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of [ams3626g](http://www.sae.org/technical/standards/AMS3626G)

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3626G>**

1. SCOPE:

1.1 Form:

This specification covers one type of methyl methacrylate resin in the form of extrusions, compression moldings, and injection moldings.

1.2 Application:

These products have been used typically for parts requiring good dimensional stability, a high degree of optical clarity, and good resistance to outdoor weathering, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The applicable issue of referenced publications shall be the issue in effect on the date of the purchase order.

SAENORM.COM : Click to view the full PDF of AMS3626G

2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor, West Conshohocken, PA 19428-2959.

ASTM D 256	Impact Resistance of Plastics and Electrical Insulating Materials
ASTM D 570	Water Absorption of Plastics
ASTM D 635	Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position
ASTM D 638	Tensile Properties of Plastics
ASTM D 638M	Tensile Properties of Plastics (Metric)
ASTM D 648	Deflection Temperature of Plastics Under Flexural Load
ASTM D 792	Specific Gravity (Relative Density) and Density of Plastics by Displacement

2.2 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be an unfilled methyl methacrylate resin.

3.2 Color:

Colorless, transparent, or, when specified, the product shall be furnished translucent or opaque and in the color specified.

3.3 Properties:

The product shall conform to the requirements specified in Table 1, 3.3.7, and 3.3.8; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

TABLE 1 - Properties

Paragraph	Property	Requirement	Test Method
3.3.1	Tensile Strength, minimum at 23 °C ± 1 (73 °F ± 2) at 70 °C ± 1 (158 °F ± 2)	7600 psi (52.4 MPa) 2800 psi (19.3 MPa)	ASTM D 638 or ASTM D 638M Speed C
3.3.2	Impact Strength, Notched Izod, minimum at 23 °C ± 1 (73 °F ± 2)	0.2 foot-pound per inch (10.7 J/m)	ASTM D 256, Method A
3.3.3	Specific Gravity at 23/23 °C (73/73 °F), maximum	1.19	ASTM D 792, Method A
3.3.4	Water Absorption (24 hours immersion) at 23 °C ± 1 (73 °F ± 2) Gain, maximum Soluble Loss, maximum	0.60% 0.12%	ASTM D 570
3.3.5	Deflection Temperature at 264 psi (182 kPa) fiber stress, minimum	65 °C (149 °F)	ASTM D 648
3.3.6	Rate of Burning, maximum (See 8.2)	1.5 inches per minute (0.6 mm/s)	ASTM D 635

3.3.7 Weather Resistance: The product shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and vendor.

3.3.8 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, and free from imperfections detrimental to usage of the product.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for tensile strength (3.3.1), impact strength (3.3.2), and specific gravity (3.3.3) are acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 When the product is of such size or configuration that suitable specimens cannot be obtained, separate specimens shall be supplied upon request. Such specimens shall be molded from the same batch of powder and under conditions representative of those used in making the product.

4.3.1.2 A lot shall be all product of the same size and configuration or the same part number from the same batch of molding powder produced in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 200 pounds (91 kg).

4.3.1.3 A batch of molding powder shall be all powder produced in one continuous set of operations.

4.3.1.4 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.3.1.5 Specimens for impact strength (3.3.2) shall be nominally 1/2 by 1/8 inch (12.7 by 3.2 mm).

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.3.2.1 Specimens for rate of burning (3.3.6) shall be nominally 1/8 inch (3.2 mm) thick.

4.4 Approval:

4.4.1 Sample product shall be approved by purchaser before product for production use is supplied, unless such approval be waived by purchaser. Results of tests on production product shall be essentially equivalent to those on the approved sample product.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production product which are essentially the same as those used on the approved sample product. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested by purchaser, sample product. Production product made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 3626G, vendor's compound number, form, size or part number, and quantity.

4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Product Identification:

5.1.1 Moldings: Each molding of suitable size shall have the part number molded or permanently impressed therein. If size or configuration precludes integral marking, moldings of each different part number shall be packaged in separate, suitable containers marked with the part number.

5.1.2 Extrusions: Each extrusion shall be marked near one end or, if coiled, near the outside end with the manufacturer's designation and AMS 3626G.