

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4125K

Issued 1939-12
Revised 2001-05
Noncurrent 2009-08

Superseding AMS4125J

Aluminum Alloy Die Forgings, and Rolled or Forged Rings
0.9Si – 0.62Mg – 0.25Cr (6151-T6)
Solution and Precipitation Heat Treated

(Composition similar to UNS A 96151)

RATIONALE

AMS4125K results from a Five Year Review and update of this specification. A survey of producers found no new designs being quoted with this material/product. Accordingly, this document has been designated Non-Current.

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of August 2009. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which may have been widely used previously and which may be required for production or processing of existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs.

"NONCURRENT" specifications are available from SAE upon request.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2009 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4125K>**

 SAE The Engineering Society For Advancing Mobility Land Sea Air and Space® INTERNATIONAL® 400 Commonwealth Drive, Warrendale, PA 15096-0001	AEROSPACE MATERIAL SPECIFICATION	SAE AMS 4125J								
Issued DEC 1939 Revised MAY 2001 Reaffirmed APR 2006 Superseding AMS 4125H										
Aluminum Alloy Die Forgings, and Rolled or Forged Rings 0.9Si - 0.62Mg - 0.25Cr (6151-T6) Solution and Precipitation Heat Treated (Composition similar to UNS A 96151)										
1. SCOPE: 1.1 Form: This specification covers an aluminum alloy in the form of die forgings, rolled or forged rings, and stock for forgings and rings. 1.2 Application: These products have been used typically for complex-shaped parts requiring moderate strength and good forgeability of the material, but usage is not limited to such applications. Corrosion resistance of this alloy is superior to that of the copper-containing alloys. 2. APPLICABLE DOCUMENTS: The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply. 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001. <table border="0"> <tr> <td>AMS 2355</td> <td>Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings</td> </tr> <tr> <td>MAM 2355</td> <td>Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units</td> </tr> <tr> <td>AMS 2772</td> <td>Heat Treatment of Aluminum Alloy Raw Materials</td> </tr> <tr> <td>AMS 2808</td> <td>Identification, Forgings</td> </tr> </table>			AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings	MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units	AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials	AMS 2808	Identification, Forgings
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings									
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units									
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials									
AMS 2808	Identification, Forgings									

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

AMS 4125J**SAE****AMS 4125J****2.2 ASTM Publications:**

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications

ASTM B 660 Packing/Packaging of Aluminum and Magnesium Products

ASTM E 1417 Liquid Penetrant Examination

2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

TABLE 1 - Composition

Element	min	max
Silicon	0.6	1.2
Iron	--	1.0
Copper	--	0.35
Manganese	--	0.20
Magnesium	0.45	0.8
Chromium	0.15	0.35
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Die Forgings and Rolled or Forged Rings: Solution and precipitation heat treated in accordance with AMS 2772 to the T6 temper.

AMS 4125J**SAE****AMS 4125J**

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements, determined on the mill produced size in accordance with AMS 2355 or MAM 2355 and as specified herein.

3.3.1 Forgings:

3.3.1.1 Tensile Properties: Shall be as follows:

3.3.1.1.1 Die Forgings:

3.3.1.1.1.1 With Grain Flow: Specimens, machined from forgings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with axis of specimen in area of gage length varying not more than 15 degrees from parallel to the forging flow lines, shall meet the requirements shown in Table 2:

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	44.0 ksi (303 MPa)
Yield Strength at 0.2% Offset	37.0 ksi (255 MPa)
Elongation in 4D	10%
in 5D	9%

3.3.1.1.1.2 Across Grain Flow: Specimens machined from forgings not over 4 inches (102 mm) in nominal thickness at time of heat treatment with axis of specimen in area of gage length varying not more than 15 degrees from perpendicular to the forging flow lines, shall have the properties shown in Table 3:

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	44.0 ksi (303 MPa)
Yield Strength at 0.2% Offset	37.0 ksi (255 MPa)
Elongation in 4D	6%
in 5D	5%

AMS 4125J

SAE

AMS 4125J

3.3.1.1.2 Rolled or Forged Rings:

- 3.3.1.1.2.1 Tangential: Specimens, machined from rings not over 2.5 inches (63.5 mm) in nominal thickness at time of heat treatment with axis of specimen tangential to the ring circumference (approximately parallel to the direction of rolling), shall have the properties shown in Table 4:

TABLE 4 - Minimum Tensile Properties

Property	Value
Tensile Strength	44.0 ksi (303 MPa)
Yield Strength at 0.2% Offset	37.0 ksi (255 MPa)
Elongation in 4D	5%
in 5D	4%

- 3.3.1.1.2.2 Axial: Specimens, machined from rings not over 2.5 inches (63.5 mm) in nominal thickness at time of heat treatment with axis of specimen parallel to axis of ring (transverse to direction of rolling), shall have the properties shown in Table 5:

TABLE 5 - Minimum Tensile Properties

Property	Value
Tensile Strength	44.0 ksi (303 MPa)
Yield Strength at 0.2% Offset	35.0 ksi (241 MPa)
Elongation in 4D	4%
in 5D	3%

- 3.3.1.1.3 Test Specimens: Specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated die forgings, shall have the properties shown in Table 6:

TABLE 6 - Minimum Tensile Properties

Property	Value
Tensile Strength	44.0 ksi (303 MPa)
Yield Strength at 0.2% Offset	37.0 ksi (255 MPa)
Elongation in 4D	14%
in 5D	12%

AMS 4125J**SAE****AMS 4125J**

3.3.2 Stock for Forgings or Rings: When a sample of stock is forged to a test coupon having a degree of mechanical working not greater than the forging and heat treated in the same manner as forgings or rings, specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1.1. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1.1, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Each die forging and, when specified, each rolled or forged ring shall be etched to produce a surface suitable for visual inspection. Surface shall be evaluated for defects and, if defects can be removed so they do not reappear on re-etching and if the required section thickness is maintained, the forgings and rings are acceptable.

3.4.1.1 When approved by purchaser, a sampling plan may be used in lieu of etching each die forging and/or ring.

3.4.2 When specified, die forgings and rolled or forged rings shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417 and/or ultrasonic inspection in accordance with ASTM B 594. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings, showing no evidence of re-entrant grain flow.

3.5 Tolerances:

Forging stock shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: The following requirements are acceptance tests and, except for composition, shall be performed on each lot:

4.2.1.1 Composition (3.1).