



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS 5036F

Superseding AMS 5036E

Issued 4-1-43  
Revised 7-16-79

### STEEL SHEET AND STRIP, ALUMINUM COATED Low Carbon

#### 1. SCOPE:

- 1.1 Form: This specification covers a low-carbon steel in the form of sheet and strip which has been coated on both faces with an aluminum-silicon alloy by the hot-dip process.
- 1.2 Application: Primarily for low-stressed parts, such as brackets, clips, and sheathing, requiring corrosion resistance and oxidation resistance up to 1200°F (650°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

##### 2.1.1 Aerospace Material Specifications:

AMS 2232 - Tolerances, Carbon Steel Sheet, Strip, and Plate  
AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels  
AMS 2350 - Standards and Test Methods  
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B117 - Salt Spray (Fog) Testing  
ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials  
ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

##### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

##### 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and published by SAE, are advisory only. Their use by anyone engaged in industry or trade or this use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

### 3. TECHNICAL REQUIREMENTS:

#### 3.1 Composition:

- 3.1.1 Basis Steel: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.10
Manganese	0.25 -	0.50
Phosphorus	--	0.04
Sulfur	--	0.05

- 3.1.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

- 3.1.2 Coating: Shall consist of a uniform layer of an aluminum-silicon (5 - 11% silicon) alloy on each side of the steel sheet or strip.

- 3.2 Condition: Aluminum killed, cold rolled, and rerolled after coating.

- 3.3 Properties: The product shall conform to the following requirements:

- 3.3.1 Corrosion Resistance: The product shall show no evidence of corrosion of the basis steel when subjected for not less than 200 hr to a continuous salt spray corrosion test in accordance with ASTM B117. Corrosion of basis steel at cut edges shall be disregarded.

- 3.3.2 Bending Properties: Shall be as follows, determined in accordance with ASTM E290:

- 3.3.2.1 The product shall withstand, without flaking or peeling of the coating on the outside of the bend, bending at room temperature in any direction through an angle of 180 deg over a diameter equal to twice the nominal thickness of the product.

- 3.3.2.2 The product shall withstand, without cracking of the basis steel, bending at room temperature in any direction through an angle of 180 deg flat on itself.

- 3.3.3 Coating Weight: Shall be 0.30 - 0.50 oz per sq ft (94.5 - 158 g/m<sup>2</sup>), determined as in 3.3.3.1 on specimens as in 4.3.1.

- 3.3.3.1 Each specimen (4.3.1) shall be cleaned by washing thoroughly in petroleum ether or other suitable solvent, dried thoroughly, and weighed to the nearest 0.005 gram. Immerse each specimen in hot (approximately 150°F (65°C)) 20% sodium hydroxide solution until evolution of gases ceases. Remove specimens, scrub under running water, blot with a towel to remove the water, and immerse for 2 - 3 sec in cold concentrated hydrochloric acid. Remove specimens from the acid, scrub under running water, and reimmerse in the sodium hydroxide solution until action again ceases. Repeat this cycle until immersion in the sodium hydroxide shows no visible reaction. Remove the specimens, scrub under running water, dry, and reweigh. The loss in weight in grams is equal to the weight of coating in oz per sq ft (0.315 kg/m<sup>2</sup>).

- 3.3.3.1.1 In the above procedure it is very important that the water be removed from the surface of the specimens before immersion in the hydrochloric acid since diluted hydrochloric acid will attack the base metal to a greater extent than the concentrated acid.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5 Tolerances: Unless otherwise specified, tolerances, except as specified in 3.5.1, shall conform to all applicable requirements of AMS 2232.
- 3.5.1 Thickness: Shall be as specified in Table I.

TABLE I

Nominal Thickness Inch	Tolerance, Inch plus and minus
Up to 0.020, incl	0.003
Over 0.020 to 0.029, incl	0.004
Over 0.029 to 0.049, incl	0.005
Over 0.049 to 0.069, incl	0.006
Over 0.069 to 0.079, incl	0.007
Over 0.079 to 0.089, incl	0.008
Over 0.089 to 0.1875, excl	0.009

TABLE II

Nominal Thickness Millimetres	Tolerance, Millimetre plus and minus
Up to 0.51, incl	0.08
Over 0.51 to 0.74, incl	0.10
Over 0.74 to 1.24, incl	0.13
Over 1.24 to 1.75, incl	0.15
Over 1.75 to 2.01, incl	0.18
Over 2.01 to 2.26, incl	0.20
Over 2.26 to 4.762, excl	0.23

#### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.
- 4.3 Sampling: Shall be in accordance with AMS 2370.
- 4.3.1 Specimens for coating weight determination (3.3.3) shall be approximately 2-1/4 in. (57 mm) square or 5.06 sq in. (32.7 cm<sup>2</sup>); weight losses shall be corrected for the actual area of the specimens. Three specimens shall be cut to represent each sample sheet or strip; one of these specimens shall be cut to represent the center and the other two specimens from diagonally opposite corners of the sample. The corner specimens shall be at least 4 in. (100 mm) from the end and at least 2 in. (50 mm) from the side of the sheet or strip.

- 4.3.1.1 Product Over 12 in. (305 mm) in Nominal Width: Cut specimens from one flat sheet or strip from each lot. For coiled product, cut a sample approximately 18 in. (455 mm) long by the full width of the coil from one end of the coil and cut the specimens from this sample.
- 4.3.1.2 Product 12 In. (305 mm) and Under in Nominal Width: Cut samples not less than 18 in. (455 mm) long from one end of one to three coils or flat sheets or strips, as applicable, from each lot. Cut specimens from the sample or samples, observing the end distance and, insofar as width permits, the edge distance requirements of 4.3.1.

4.4 Reports:

- 4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat of basis steel and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

Ø 4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: The product shall be identified as in 5.1.1 unless purchaser permits a method from 5.1.2.
- 5.1.1 Each sheet and strip shall be marked on one face, in the respective location indicated below, with AMS 5036F, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked.
- 5.1.1.1 Flat Strip 6 In. (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm).
- 5.1.1.2 Flat Sheet and Strip Over 6 In. (152 mm) in Width: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm), the rows being spaced not more than 6 in. (152 mm) apart and alternately staggered.
- 5.1.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.1. When the inside end of the coil is inaccessible, as when the product is wound on cores, the tag or label may be attached to the core.
- Ø
- 5.1.2 When purchaser permits, each sheet and strip may be marked near one end, coils being marked near the outside end, with AMS 5036F, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternate method, individual pieces and bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.