



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

AMS 5512D

Superseding AMS 5512C

Issued 9-1-47
Revised 5-15-71

STEEL SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT 18Cr - 10.5Ni - (Cb + Ta) (SAE 30347)

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant steel in the form of sheet, strip, and plate.
- 1.2 Application: Primarily for parts and assemblies requiring both corrosion and heat resistance and especially when such parts and assemblies are welded during fabrication. Parts and assemblies requiring oxidation resistance up to approximately 1500 F (816 C), but useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply; the applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel and Iron Base Alloy Sheet,

Strip, and Plate and Titanium and Titanium Alloy Sheet, Strip, and Plate

AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM A393 - Conducting Acidified Copper Sulfate Test for Intergranular Attack in Austenitic Stainless Steel

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 Government Publications: Available from Superintendent of Documents, Government Printing Office, Washington, D. C. 20402.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods.

SAE Technical Board rules provide that: "All technical reports, including standards, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.50 -	1.00
Phosphorus	--	0.040
Sulphur	--	0.030
Chromium	17.00 -	19.00
Nickel	9.00 -	12.00
Columbium + Tantalum	10xC	1.10
Molybdenum	--	0.75
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Sheet: Cold rolled, solution heat treated, and descaled (No. 2D Finish).

3.2.2 Strip: Cold rolled, solution heat treated, and descaled (No. 1 Strip Finish).

3.2.3 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Properties:

3.3.1 Tensile Properties: Shall be as specified in Table I determined in accordance with ASTM A370:

TABLE I

Nominal Thickness Inches	Tensile Strength psi, max	Elongation % in 2 in. or 4D, min
Over 0.002 to 0.003, incl	115,000	20
Over 0.003 to 0.004, incl	110,000	30
Over 0.004	105,000	40

TABLE I (SI)

Nominal Thickness Millimeters	Tensile Strength MN/m ² , max	Elongation % in 50.8 mm or 4D, min
Over 0.0508 to 0.0762, incl	793	20
Over 0.0762 to 0.1016, incl	758	30
Over 0.1016	724	40

3.3.1.1 For widths 9 in. (229 mm) and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in. (229 mm), tensile test specimens shall be taken with the axis parallel to the direction of rolling.

3.3.2 Bending: Material shall withstand, without cracking, bending in accordance with ASTM A370 at room temperature through the angle indicated in Table II around a diameter equal to the bend factor times the nominal thickness of the material with axis of bend parallel to the direction of rolling.

TABLE II

Nominal Thickness Inch	Type of Bend	Angle deg, min	Bend Factor
Up to 0.249, incl	Free Bend	180	1
Up to 0.249, incl	V-Block	135	1
Over 0.249 to 0.749, incl	Free Bend	90	1
Over 0.249 to 0.749, incl	V-Block	135	2

TABLE II (SI)

Nominal Thickness Millimeters	Type of Bend	Angle rad, min	Bend Factor
Up to 6.325, incl	Free Bend	3.14	1
Up to 6.325, incl	V-Block	2.36	1
Over 6.235 to 19.024, incl	Free Bend	1.57	1
Over 6.235 to 19.024, incl	V-Block	2.36	2

3.3.3 Embrittlement: The product, after sensitizing treatment, shall be capable of being exposed to acidified copper sulfate in accordance with ASTM A393 without evidence of inter-crystalline surface attack and, after exposure, of withstanding bending as in 3.3.2.

3.4 Quality: The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2242.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that material conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Routine Control Tests: Tests to determine conformance to composition (3.1), condition (3.2), tensile property (3.3.1), bending (3.3.2), and tolerance (3.5) requirements are classified as routine control tests.

4.2.2 Periodic Control Tests: Tests to determine conformance to embrittlement (3.3.3) requirements are classified as qualification and/or periodic control tests.

4.3 Sampling: Shall be in accordance with AMS 2371.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and for tensile and bending properties of each size from each heat. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.