

AEROSPACE MATERIAL SPECIFICATION

Issued 1952-06
Revised 2005-11
Reaffirmed 2010-10

Superseding AMS 5576J

Steel, Corrosion and Heat-Resistant, Welded Tubing
18Cr - 10.5Ni - 0.40Ti (SAE 30321)
Solution Heat Treated
(Composition similar to UNS S32100)

RATIONALE

K Revision — To conduct a Five Year Review.

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant steel in the form of welded tubing.

1.2 Application:

This tubing has been used typically for parts requiring both corrosion and heat resistance, especially when subjected to welding, brazing, or other exposure to temperatures over 800 °F (427 °C) during fabrication, and also for parts requiring oxidation resistance up to 1500 °F (816 °C) but useful at that temperature only when stresses are low. Usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5576K>**

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2243	Tolerances, Corrosion and Heat-Resistant Steel Tubing
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A 262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.25	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00	19.00
Nickel	9.00	12.00
Titanium	5x(C+N)	0.70
Molybdenum	--	0.75
Copper	--	0.75
Nitrogen	--	0.10

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

Solution heat treated and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled.

3.3 Fabrication:

Tubing 2.00 inches (50.8 mm) and under in nominal OD shall be cold worked after welding. Finishing operations for removal of surface blemishes shall be performed prior to final solution heat treatment. A light polish to improve surface appearance may be employed after solution heat treatment.

3.4 Properties:

Tubing shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal OD Inch	Nominal Wall Thickness Inch	Tensile Strength ksi, max	Elongation in 2 inches %, min Strip	Elongation in 2 inches %, min Full Tube
Up to 0.188, incl	Up to 0.016, incl	120	--	33
	Over 0.016	105	--	35
Over 0.188 to 0.500, incl	Up to 0.010, incl	115	30	35
	Over 0.010	105	30	35
Over 0.500	Up to 0.010, incl	120	25	30
	Over 0.010	105	30	35

TABLE 2B - Tensile Properties, SI Units

Nominal OD Millimeters	Nominal Wall Thickness Millimeter	Tensile Strength MPa, max	Elongation in 50.8 mm %, min Strip	Elongation in 50.8 mm %, min Full Tube
Up to 4.78, incl	Up to 0.41, incl	827	--	33
	Over 0.41	724	--	35
Over 4.78 to 12.70, incl	Up to 0.25, incl	793	30	35
	Over 0.25	724	30	35
Over 12.70	Up to 0.25, incl	827	25	30
	Over 0.25	724	30	35

- 3.4.2 Flarability: Specimens as in 4.3.1 shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 degree included angle to produce a flare having a permanent expanded OD not less than specified in Table 3.

TABLE 3A - Flarability, Inch/Pound Units

Nominal OD Inch	Expanded OD Inch	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

TABLE 3B - Flarability, SI Units

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
3.18	5.08	19.05	23.80
4.78	7.67	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84		

- 3.4.2.1 Tubing with nominal OD between any two standard sizes given in Table 3 shall take the same percentage flare as that for the larger of the two sizes.
- 3.4.3 Susceptibility to Intergranular Attack: Specimens from tubing, after sensitizing treatment and immersion as required by ASTM A 262 Practice E, shall not exhibit intergranular attack or cracks when tested in accordance with the following:
- 3.4.3.1 Examination of OD Surface: Shall be performed after flattening a 1-inch (25 mm) long specimen to a total thickness under load of three times the wall thickness.
- 3.4.3.2 Examination of ID Surface: Shall be performed after splitting a 1-inch (25-mm) long specimen and folding the split specimen, with ID surfaces on the outside of fold, around a mandrel having a diameter equal to the nominal wall thickness of the tube.
- 3.4.3.2.1 Tubing Over 0.625 Inch (15.88 mm) in OD: The axis of the fold shall be parallel to the axis of the tube.
- 3.4.3.2.2 Tubing 0.625 Inch (15.88 mm) and Under in OD: The axis of the fold shall be either parallel or transverse to the axis of the tube.

- 3.4.3.3 If a weld is visible, flattening and/or folding parallel to the tube axis shall be oriented so as to apply maximum tension to the weld.

3.5 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

- 3.6 If beads are present at the welds on the inner surfaces of tubing over 2.00 inches (50.8 mm) in nominal OD, such beads shall be not thicker than 0.010 inch (0.25 mm). The outer surfaces of all tubing and the inner surfaces of tubing 2.00 inches (50.8 mm) and under in nominal OD shall be free from beads.

3.7 Tolerances:

Shall conform to all applicable requirements of AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.4.1), and tolerances (3.7) are acceptance tests and shall be performed on each heat or lot as applicable.

- 4.2.2 Periodic Tests: Flarability (3.4.2) and susceptibility to intergranular attack (3.4.3) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371 and the following:

- 4.3.1 Specimens for flarability test (3.4.2) shall be full tubes or sections cut from a tube. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.