



AEROSPACE MATERIAL SPECIFICATION

AMS5582™

REV. H

Issued 1959-06
Reaffirmed 2011-08
Revised 2024-05

Superseding AMS5582G

(R) Nickel Alloy, Corrosion- and Heat-Resistant
Seamless Tubing,
72Ni - 15.5Cr - 0.95Cb (Nb) - 2.5Ti - 0.70Al - 7.0Fe (X750),
Solution Heat Treated, Precipitation Hardenable
(Composition similar to UNS N07750)

RATIONALE

AMS5582H is the result of a Five-Year Review and update of the specification. The revision updates the title to be consistent with other specifications, clarifies definitions (see 2.3), updates composition testing and reporting (see 3.1 and 3.1.2), revises condition and fabrication requirements (see 3.2 and 3.4), adds strain rate control during tensile testing (see 3.5.2.1.1), prohibits unauthorized exceptions (see 3.5.3 and 8.4), updates quality and inspection requirements adding nondestructive testing methods (see 3.6.1, 3.6.2, 3.6.3, 4.2.2, and 8.5), and clarifies identification requirements (see 5.2.1).

1. SCOPE

1.1 Form

This specification covers a precipitation hardenable, corrosion- and heat-resistant nickel alloy in the form of seamless tubing 0.125 inch (3.18 mm) and over in nominal OD and 0.015 inch (0.38 mm) and over in nominal wall thickness.

1.2 Application

This tubing has been used typically for fluid lines requiring high strength up to 1300 °F (704 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications. Parts may be formed and then heat treated to improve strength at elevated temperatures.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)

Tel: +1 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: CustomerService@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

For more information on this standard, visit

<https://www.sae.org/standards/content/AMS5582H/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2263	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Aircraft Tubing
AMS2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys
AMS2283	Composition Testing Methods for Nickel and Cobalt Based Alloys
AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2634	Ultrasonic Inspection, Thin Wall Metal Tubing
AMS2750	Pyrometry
AMS2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys Sheet, Strip, Plate, and Aircraft Tubing
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B751	Nickel and Nickel Alloy Welded Tube
ASTM B829	Nickel and Nickel Alloys Seamless Pipe and Tube
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E112	Determining Average Grain Size
ASTM E426	Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Titanium, Austenitic Stainless Steel and Similar Alloys
ASTM E1417/E1417M	Liquid Penetrant Testing

2.3 Terms used in AMS are defined in AS7766 and the following:

2.3.1 Bore conditioning is any mechanical cleaning method that is used in the bore of tubing to improve the final surface appearance, with no resultant change in tubing size beyond the allowable tolerances.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2283 or by other analytical methods acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.08
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.010
Chromium	14.00	17.00
Nickel	70.00	--
Columbium (Niobium)	0.70	1.20
Titanium	2.25	2.75
Aluminum	0.40	1.00
Iron	5.00	9.00
Cobalt (3.1.1)	--	1.00
Tantalum	--	0.05
Copper	--	0.50

3.1.1 Determination not required for lot acceptance.

3.1.2 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.3 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Condition

Solution heat treating shall be performed in an atmosphere yielding a bright finish. Alternately, product shall be chemically cleaned to produce a uniform finish. It is permissible to pickle prior to final cleaning treatment. Final chemical cleaning may take place after any final finishing (see 3.4.3). After final chemical cleaning is performed, tube cleanliness shall be verified using the corrosion resistance test methods specified in AMS2700 for Class 2 parts or alternate method acceptable to the purchaser.

3.3 Heat Treatment

Tubing shall be solution heat treated by heating to a temperature not lower than 1800 °F (982 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster. Pyrometry shall be in accordance with AMS2750.

3.4 Fabrication

3.4.1 Tubing shall be produced by a seamless and drawn process. Surface finishing operations applied to remove objectionable pits and blemishes shall be performed prior to solution heat treatment. Only light polishing to improve external surface appearance is permitted after solution heat treatment and, if performed, the product shall be subsequently chemically cleaned.

3.4.2 Bore conditioning (see 2.3) is permitted after final anneal providing the tubing is not sized by metal removal methods beyond the original tolerances. If bore conditioning is used, 100% visual inspection of each tube shall be performed. The tube ID shall be uniformly shiny with no evidence of remnant material.

3.4.3 Tubing shall be chemically cleaned after any ID or OD finishing that occurs after heat treatment.

3.5 Properties

Tubing 0.125 inch (3.18 mm) and over in nominal OD and 0.015 inch (0.38 mm) and over in nominal wall thickness shall conform to the following requirements:

3.5.1 As Solution Heat Treated

3.5.1.1 Tensile Properties

Tensile properties shall be as shown in Table 2, determined in accordance with ASTM E8/E8M.

Table 2 - Solution heat-treated tensile properties

Property	Value
Tensile Strength, Maximum	140 ksi (965 MPa)
Yield Strength at 0.2% Offset, Maximum	80 ksi (552 MPa)
Elongation in 2 Inches (50 mm) or 4D, Minimum	
Strip Specimen	30%
Full Tube	35%

3.5.1.2 Average Grain Size

Average grain size shall be ASTM No. 2.5 or finer, determined in accordance with ASTM E112.

3.5.1.3 Flarability

Specimens as in 4.3.1 from tubing 0.188 to 2.000 inches (4.78 to 50.80 mm), inclusive, in nominal OD shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than 1.20 times the original nominal OD.

3.5.2 Response to Precipitation Heat Treatment

Tubing shall have the following properties after being precipitation heat treated by heating to $1300^{\circ}\text{F} \pm 25^{\circ}\text{F}$ ($704^{\circ}\text{C} \pm 14^{\circ}\text{C}$), holding at heat for 20 hours ± 1 hour, and cooling at a rate equivalent to cooling in air:

3.5.2.1 Tensile Properties

Response to heat-treatment tensile properties shall be as shown in Table 3, determined in accordance with ASTM E8/E8M.

Table 3 - Minimum tensile properties - response to heat treatment

Property	Value
Tensile Strength	155 ksi (1069 MPa)
Yield Strength at 0.2% Offset	100 ksi (689 MPa)
Elongation in 2 Inches (50 mm) or 4D	
Strip Specimen	15%
Full Tube	20%

3.5.2.1.1 Unless otherwise specified, the strain rate shall be set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through 0.2% offset yield strain. After the yield strain, the speed of the testing machine shall be set between 0.05 in/in and 0.5 in/in (0.05 mm/mm and 0.5 mm/mm) of the length of the reduced parallel section (or distance between the grips for specimens not having a reduced section) per minute. Alternatively, an extensometer and strain rate indicator may be used to set the strain rate between 0.05 in/in/min and 0.5 in/in/min (0.05 mm/mm/min and 0.5 mm/mm/min). The requirement for compliance becomes effective for material produced 1 year after the publication date of this specification.

3.5.3 Mechanical property requirements for tubing outside the thickness and diametral limits of 1.1 shall be as agreed upon by the purchaser and producer and reported per 4.4.5.

3.6 Quality

Tubing as received by the purchaser shall be uniform in quality and condition and shall have a finish conforming to the best practice for high-quality aircraft tubing. It shall be smooth and free from grease, oil, and other foreign matter, heavy scale or oxide, burrs, seams, tears, cracks, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, and scale pattern are considered acceptable if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

3.6.1 A clean white cloth or plug drawn or blown through the length of the bore of a test sample at least 12 inches (30 cm) in length, shall show no visual evidence of metallic flakes or particles. Discoloration of the cloth or plug, without the presence of flakes or particles, is acceptable. Alternate methods for evaluating tube cleanliness may be used for tubing 0.500 inch (12.7 mm) and under ID.

3.6.2 When no inspection is specified by the purchaser, tubing shall be subjected to either ultrasonic or eddy current inspection in accordance with ASTM B751 or ASTM B829 except that suspect indications shall not be accepted based on visual observation (i.e., indications must be either rejected or reconditioned and retested to pass the test). Alternate methods of inspection may be used for tube 0.25 inch (0.64 cm) and under in nominal diameter.

3.6.3 When specified by the purchaser (see 8.5), tubing shall be subjected to fluorescent penetrant inspection in accordance with ASTM E1417/E1417M, to ultrasonic inspection in accordance with AMS2634, to electromagnetic (eddy-current) inspection in accordance with ASTM E426, or to any combination thereof. Tubing shall meet the requirements of acceptance criteria established by the cognizant engineering organization.

3.7 Tolerances

Tolerances shall conform to all applicable requirements of AMS2263.

3.8 Exceptions

Any exception shall be authorized by the purchaser and reported as in 4.4.5.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (see 3.1), tensile properties (see 3.5.1.1), response to precipitation heat treatment (see 3.5.2.1), average grain size (see 3.5.1.2), and tolerances (see 3.7) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Nondestructive inspection per 3.6.2 shall be performed on each finished tube or as specified (see 3.6.3). The requirements of 3.6.2 shall become effective 1 year after the publication date of this document.

4.2.3 Periodic Tests

Flarability (see 3.5.1.3) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.