



AEROSPACE MATERIAL SPECIFICATION

AMS5836™**REV. D**

Issued 1990-04
Reaffirmed 2006-04
Revised 2015-12

Superseding AMS5836C

Nickel Alloy, Corrosion and Heat-Resistant, Welding Wire
72Ni - 3.0Mn - 20Cr - 2.5Cb(Nb)
(Composition similar to UNS N06082)

RATIONALE

AMS5836D has been updated to incorporate the standard quality requirements of AMS materials as the ordering requirements for AWS specified wire and is a Five Year Review and of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of parts fabricated from high nickel alloys or combinations of such alloys and corrosion-resistant or plain-carbon steels, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2813 Packaging and Marking of Packages of Welding Wire, Standard Method

AMS2814 Packaging and Marking of Packages of Welding Wire, Premium Quality

AMS2816 Identification Welding Wire, Tab Marking Method

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5836D>**

AMS2819 Identification Welding Wire, Direct Color Code System

ARP4926 Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 AWS Publications

Available from American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33166-6672, Tel: 1-800-443-9353 or 305-443-9353, www.aws.org.

AWS A5.01 Welding Consumables – Procurement of Filler Metals and Fluxes

AWS A5.14 Specification for Nickel and Nickel-Alloy Bare Welding Electrodes and Rods

3. TECHNICAL REQUIREMENTS

3.1 Composition

Wire shall meet the technical requirements of AWS A5.14 ERNiCr-3 with the following additional chemistry controls:

Cobalt shall be 0.12 max and Tantalum shall be 0.30 max.

3.2 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances specified in AWS A5.14. Smaller diameter wires when ordered shall be supplied in sizes and tolerances shown in 3.2.1.

3.2.1 Diameter

Shall be as shown in Table 1.

Table 1A - Sizes and diameter tolerances, inch/pound units

Form	Nominal Diameter Inch	Tolerance Inch Plus	Tolerance Inch Minus
Cut Lengths	0.030, 0.035, 0.045	0.001	0.002
Spools	0.007, 0.010, 0.015	0.0005	0.0005

Table 1B - Sizes and diameter tolerances, SI units

Form	Nominal Diameter Millimeters	Tolerance Millimeter Plus	Tolerance Millimeter Minus
Cut Lengths	0.76, 0.89, 1.14	0.025	0.05
Spools	0.18, 0.25, 0.38	0.013	0.013

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of wire shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), sizes and tolerances (3.2), and alloy verification (5.1) are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with AWS A5.01 S3, testing schedule 5 or J.

4.4 Reports

The producer of wire shall furnish with each shipment a report showing the results of tests for composition of each heat, and stating that the wire conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5836D, nominal size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AWS A5.01.

5. PREPARATION FOR DELIVERY

5.1 Alloy Verification

5.1.1 Wire from each spool or package of cut lengths shall be alloy verified by a method acceptable to purchaser and producer. The alloy verification methods of ARP4926 are recommended.

5.1.2 An 8 inch (203 mm) length of wire shall be made accessible at both ends of each spool for alloy verification.

5.2 Identification

Shall be in accordance with AMS2816 unless AMS2819 or another method is specified by purchaser.

5.3 Packaging and Marking

Shall be in accordance with AMS2813 unless AMS2814 or another method is specified by purchaser.

6. ACKNOWLEDGMENT

A producer shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Wire not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.