



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 6512A

Superseding AMS 6512

Issued 5-1-70
Revised 10-16-78

STEEL BARS, FORGINGS, TUBING, AND RINGS

18Ni - 7.8Co - 4.9Mo - 0.40Ti - 0.10Al

Premium Quality, Consumable Electrode Melted, Annealed

1. SCOPE:

- 1.1 Form: This specification covers a premium-quality, alloy steel in the form of bars, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.
- 1.2 Application: Primarily for parts, such as pressure vessels, requiring through hardening, without quenching, to a minimum yield strength of 240,000 psi (1655 MPa) and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and Aerospace Standards (AS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys
AMS 2251 - Tolerances, Low-Alloy Steel Bars
AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
AMS 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS 2350 - Standards and Test Methods
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
AMS 2375 - Control of Forgings Requiring First-Article Approval
AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
AMS 2808 - Identification, Forgings
AMS 7496 - Rings, Flash Welded, Carbon and Low-Alloy Steels

2.1.2 Aerospace Standards:

AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM A604 - Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets

ASTM E45 - Determining the Inclusion Content of Steel

ASTM E112 - Estimating the Average Grain Size of Metals

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

ASTM E399 - Plane-Strain Fracture Toughness of Metallic Materials

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

- 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.03
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.010
Nickel	17.00 - 19.00	
Cobalt	7.00 - 8.50	
Molybdenum	4.60 - 5.20	
Titanium	0.30 - 0.50	
Aluminum	0.05 - 0.15	
Chromium	--	0.50
Copper	--	0.50

- 3.1.1 Additives: Prior to pouring, up to 0.05% calcium, 0.02% zirconium, and 0.003% boron shall be added to the air melted heat; analysis for these elements need not be made.

- 3.1.2 Check Analysis: Composition variations shall meet the requirement of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars, Forgings, Mechanical Tubing, and Flash Welded Rings: Annealed and descaled.

3.2.1.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7496.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment: Bars, forgings, mechanical tubing, and flash-welded rings shall be annealed by heating to a temperature within the range 1500° - 1700° F (815° - 925° C), holding at the selected temperature within $\pm 25^{\circ}$ F ($\pm 15^{\circ}$ C) for 1 - 2 hr, and cooling in air to room temperature.

3.4 Properties: The product shall conform to the following requirements; hardness and tensile testing $\emptyset$ shall be performed in accordance with ASTM A370:

3.4.1 Heat of Steel:

3.4.1.1 Micro-Inclusion Rating: Two-thirds of the total number of specimens, as well as the average of all specimens, shall not exceed the following limits, determined in accordance with ASTM E45, Method D, except that the length of any inclusion shall be not greater than 0.015 in. (0.38 mm):

$\emptyset$	Type	Inclusion Rating				
		A	B	C	D	E
	Thin	1.5	1.5	1.5	2.0	3.0
	Heavy	1.0	1.0	1.0	1.5	1.5

$\emptyset$ 3.4.1.1.1 Type E is titanium nitrides and shall be rated in the same manner as Type B.

3.4.1.2 Macrostructure: Visual examination of transverse sections from bars, billets, tube rounds or tubes, and stock for forging or flash welded rings, etched in accordance with ASTM A604 in a suitable etchant for sufficient time to develop a well-defined macrostructure, shall show no imperfections, such as pipe, cracks, porosity, segregation, and inclusions, detrimental to fabrication or to performance of parts. Except as specified in 3.4.1.2.1 macrostructure shall be equal to or better than the following macrographs of ASTM A604:

$\emptyset$	Class	Condition	Severity
	1	Freckles	A
	2	White Spots	B
	3	Radial Segregation	B
	4	Ring Pattern	C

3.4.1.2.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

3.4.2 Bars, Wire, Forgings, Tubing, and Flash Welded Rings:

3.4.2.1 As Annealed:

3.4.2.1.1 Hardness: Bars over 0.500 in. (12.70 mm) in nominal diameter or distance between parallel sides, forgings, tubing, and flash welded rings shall have hardness not higher than 321 HB or equivalent.

3.4.2.1.2 Tensile Strength: Bars 0.500 in. (12.70 mm) and under in nominal diameter or distance between parallel sides shall have tensile strength not higher than 160,000 psi (1103 MPa) or equivalent hardness.

3.4.2.1.3 Grain Size: Shall be as follows, determined in accordance with ASTM E112; the procedure used shall be as agreed upon by purchaser and vendor:

3.4.2.1.3.1 Product Less than 2.50 In. (63.5 mm) in Nominal Section Thickness: Predominantly 6 or finer with occasional grains as large as 4 permissible.

3.4.2.1.3.2 Product 2.50 to 10.00 In. (63.5 to 254.0 mm), Incl, in Nominal Section Thickness: Predominantly 4 or finer with occasional grains as large as 2 permissible.

3.4.2.1.3.3 Product Over 10.00 In. (254.0 mm) in Section Thickness: As agreed upon by purchaser and vendor.

3.4.2.2 After Maraging: Test specimens as in 4.3 shall have the following properties after being maraged by heating to $900^{\circ}\text{F} \pm 10$ ($480^{\circ}\text{C} \pm 5$), holding at heat for 4 - 6 hr, and cooling to room temperature:

3.4.2.2.1 Tensile Properties: Shall be as specified in Table I and 3.4.2.2.1.1.

TABLE I

Nominal Section Thickness Ø Inches	Specimen Orientation	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 4D %, min	Reduction of Area %, min
Up to 4.000, excl	Longitudinal	255,000	250,000	6	45
	Transverse	255,000	250,000	4	35
4.000 to 10.000, incl	Longitudinal	245,000	240,000	5	30
	Transverse	245,000	240,000	3	20

TABLE I (SI)

Nominal Section Thickness Ø Millimetres	Specimen Orientation	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 4D %, min	Reduction of Area %, min
Up to 101.60, excl	Longitudinal	1758	1724	6	45
	Transverse	1758	1724	4	35
101.60 to 254.00, incl	Longitudinal	1689	1655	5	30
	Transverse	1689	1655	3	20

3.4.2.2.1.1 Tensile property requirements for product over 10.000 in. (254.00 mm) in nominal section thickness shall be as agreed upon by purchaser and vendor.

3.4.2.2.1.2 Longitudinal requirements apply to specimens taken with axis of specimens approximately parallel to the grain flow and to specimens taken in the radial direction and in the tangential direction at the rim of disc forgings. All other specimens shall be considered to be in the transverse direction.

3.4.2.2.1.3 Transverse test requirements apply only to product from which tensile test specimens not less than 2.50 in. (63.5 mm) in length can be taken.

3.4.2.2.1.4 Tensile properties in the longitudinal direction need not be determined on product tested in the transverse direction.

- 3.4.2.2.2 Hardness: Should be not lower than 48 HRC or equivalent but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.
- 3.4.2.2.3 Fracture Toughness: When specified, product shall be subjected to fracture toughness testing. Method of test and standards for acceptance of product shall be as agreed upon by purchaser and vendor. ASTM E399 is a suggested method of test.
- 3.4.3 Stock for Forging or Flash Welded Rings: When a sample of stock is forged to a test coupon and heat treated as in 3.3 and 3.4.2.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.2.2.1 and 3.4.2.2.2 and, when specified, 3.4.2.2.3. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.2.2 conform to the requirements of 3.4.2.2.1 and 3.4.2.2.2 and, when specified, 3.4.2.2.3, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.5 Quality:
- 3.5.1 Steel shall be premium quality conforming to AMS 2300. It shall be produced by multiple melting using consumable electrode practice in the remelt cycle; at least one of the melting cycles shall be under vacuum.
- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5.2.1 Bars, tubing, and flash welded rings ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.
- 3.5.2.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.
- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars, and tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.7 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of the following:
- 3.7.1 Bars: AMS 2251.
- 3.7.2 Mechanical Tubing: AMS 2253.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: Tests of forgings to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a forging to a purchaser, when a change in material or processing requires reapproval, or when purchaser deems confirmatory testing is required.