



AEROSPACE MATERIAL SPECIFICATION

AMS6517™**REV. A**Issued 2011-03
Revised 2015-08

Superseding AMS6517

Steel, Bars, and Forgings
3.5Cr - 9.5Ni - 18Co - 1.1Mo (0.13 - 0.17C)
Double Vacuum Melted, Normalized, Annealed
(Composition similar to UNS K93061)

RATIONALE

AMS6517A results from a Five Year Review and update of this specification and revises annealed hardness, heat treatment, macrostructure, micro-inclusion rating, response to heat treatment, grain size and reporting.

1. SCOPE

1.1 Form

This specification covers a premium aircraft-quality alloy steel in the form of bars, forgings, and forging stock.

1.2 Application

These products have been used typically for carburized parts requiring high minimum core hardness with a narrow range, reduced distortion and subject to magnetic particle inspection standards, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

| | |
|---------|---|
| AMS2251 | Tolerances, Low-Alloy Steel Bars |
| AMS2259 | Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels |
| AMS2300 | Steel Cleanliness, Premium Aircraft-Quality Magnetic Particle Inspection Procedure |
| AMS2370 | Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock |
| AMS2372 | Quality Assurance Sampling and Testing Carbon and Low-Alloy Steel Forgings |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS6517A>**

| | |
|---------|--|
| AMS2750 | Pyrometry |
| AMS2806 | Identification Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys |
| AMS2808 | Identification Forgings |
| AS1182 | Standard Stock Removal Allowance Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing |

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

| | |
|-----------|--|
| ASTM A370 | Mechanical Testing of Steel Products |
| ASTM A604 | Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets |
| ASTM E45 | Determining the Inclusion Content of Steel |
| ASTM E112 | Determining Average Grain Size |
| ASTM E350 | Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron |
| ASTM E399 | Plane-Strain Fracture Toughness of Metallic Materials |

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the following percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

| Element | min | max |
|------------|------|-----------------|
| Carbon | 0.13 | 0.17 |
| Manganese | -- | 0.10 |
| Silicon | -- | 0.10 |
| Phosphorus | -- | 0.008 |
| Sulfur | -- | 0.005 |
| Chromium | 3.0 | 4.0 |
| Nickel | 9.2 | 9.8 |
| Cobalt | 17.5 | 18.5 |
| Molybdenum | 0.9 | 1.3 |
| Titanium | -- | 0.045 |
| Aluminum | -- | 0.1 |
| Vanadium | 0.04 | 0.12 |
| Oxygen | -- | 0.0020 (20 ppm) |
| Nitrogen | -- | 0.0015 (15 ppm) |

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Melting Practice

Steel shall be multiple melted using vacuum induction melting followed by vacuum arc remelting.

3.3 Condition

The product shall be supplied in the following condition unless another condition is authorized by purchaser; hardness shall be determined in accordance with ASTM A370:

3.3.1 Bars and Forgings

Normalized and annealed (see 3.4) having hardness not higher than 352 HB, or equivalent (see 8.2), as descaled. Bar shall not be cut from plate.

3.3.2 Forging Stock

As ordered by the forging manufacturer.

3.4 Heat Treatment

Bars and forgings shall be normalized by heating to $1785^{\circ}\text{F} \pm 25^{\circ}\text{F}$ ($974^{\circ}\text{C} \pm 14^{\circ}\text{C}$) for a time commensurate with section thickness, 60 minutes minimum, cooling in air to room temperature and annealed by heating to $1255^{\circ}\text{F} \pm 25^{\circ}\text{F}$ ($679^{\circ}\text{C} \pm 14^{\circ}\text{C}$) for not less than 2 hours, and cooling in air. Pyrometry shall be in accordance with AMS2750.

3.5 Properties

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.5.1 Macrostructure

Visual examination of transverse full cross-sections from bars, billets, and stock for forging, flash welded rings, or extrusions, etched in hot hydrochloric acid in accordance with ASTM A604, shall not show pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM A604 shown in Table 2.

Table 2 - Macrostructure limits

| Class | Condition | Severity |
|-------|--------------------|----------|
| 1 | Freckles | A |
| 2 | White Spots | A |
| 3 | Radial Segregation | B |
| 4 | Ring Pattern | B |

3.5.2 Micro-Inclusion Rating of Each Heat

No specimen shall exceed the limits shown in Table 3, determined in accordance with ASTM E45, Method D.

Table 3 – Micro-inclusion rating limits

| Type | A | A | B | B | C | C | D | D |
|--|------|-------|------|-------|------|-------|------|-------|
| | Thin | Heavy | Thin | Heavy | Thin | Heavy | Thin | Heavy |
| Worst Field Severity | 1.5 | 1.0 | 1.5 | 1.0 | 1.5 | 1.0 | 1.5 | 1.0 |
| Worst Field Frequency, maximum | (a) | 1 | (a) | 1 | (a) | 1 | 3 | 1 |
| Total Rateable Fields, Frequency, maximum | (b) | 1 | (b) | 1 | (b) | 1 | 8 | 1 |
| (a) Combined A+B+C; not more than 3 fields | | | | | | | | |
| (b) Combined A+B+C; not more than 8 fields | | | | | | | | |

3.5.2.1 A rateable field is defined as one that has a type A, B, C, or D inclusion rating of at least No. 1.0 thin or heavy in accordance with ASTM E45.

3.5.3 Response to Heat Treatment - Bars and Forgings

Test specimens extracted from product shall conform to the following requirements after being austenitized by heating to 1830 °F ± 25 °F (999 °C ± 14 °C), holding at heat for a time commensurate with section thickness, heating equipment, and procedure used, oil quenched (or equivalent) to below 90 °F (32 °C) followed by cooling to -100 °F (-73 °C) or lower, holding at temperature for 1 hour +2/-0, warming in air to room temperature, and tempering at 900 °F ± 10 °F (482 °C ± 6 °C) for 16 hours ± 2 hours, and cooling in air (or equivalent).

3.5.3.1 Tensile Properties

3.5.3.1.1 Longitudinal tensile properties shall be as shown in Table 4. Testing in the longitudinal direction need not be performed on product qualified by testing in the transverse orientation.

Table 4 - Minimum longitudinal tensile properties

| Property | Value |
|----------------------------|--------------------|
| Tensile Strength | 225 ksi (1551 MPa) |
| Yield Strength 0.2% Offset | 208 ksi (1434 MPa) |
| Elongation in 4D | 13% |
| Reduction of Area | 60% |

3.5.3.1.2 Transverse tensile properties shall be as shown in Table 5. Transverse properties apply only to product that a tensile specimen not less than 1.625 inches (4.128 mm) in length can be taken.

Table 5 - Minimum transverse tensile properties

| Property | Value |
|----------------------------|--------------------|
| Tensile Strength | 225 ksi (1551 MPa) |
| Yield Strength 0.2% Offset | 208 ksi (1434 MPa) |
| Elongation in 4D | 12% |
| Reduction of Area | 54% |

3.5.3.2 Hardness

Shall not be lower than 47 HRC, or equivalent (see 8.2).

3.5.3.3 Fracture Toughness

Shall be not lower than 105 ksi $\sqrt{\text{inch}}$ (116 MPa $\sqrt{\text{m}}$) K_{IC} or K_Q , determined in accordance with ASTM E399 on any product that a specimen of a standardized ASTM E399 orientation can be extracted having dimensions not less than 1.50 inches (38.1 mm) in section thickness and not less than 4.00 inches (101.6 mm) in width. Unless otherwise specified by the purchaser, the product can be tested in either the longitudinal L-T or L-R orientation or transverse T-L or R-L orientation.

3.5.3.4 Average Grain Size of Bars and Forgings

Shall be ASTM No. 5 or finer determined in accordance with ASTM E112 after austenitizing in accordance with 3.5.3.

3.5.4 Forging Stock

A sample of stock shall be forged to a test coupon acceptable to purchaser and heat treated as in 3.4 and 3.5.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.3.1, 3.5.3.2, 3.5.3.3, and 3.5.3.4. Alternately specimens taken from the stock after heat treatment as in 3.4 and 3.5.3 that conform to the requirements of 3.5.3.1, 3.5.3.2, 3.5.3.3, and 3.5.3.4 shall be accepted as equivalent to tests of a forged coupon.

3.6 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Steel shall be premium aircraft-quality conforming to AMS2300.

3.6.2 Product ordered hot finished or cold finished or ground, turned, or polished shall, after removal of the standard stock removal allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the machined, ground, turned, or polished surface.

3.6.3 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.7 Tolerances

3.7.1 Bars

In accordance with AMS2251.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1), macrostructure rating (3.5.1), and micro-inclusion rating (3.5.2) of each heat.

4.2.1.2 Annealed hardness (3.5.1) and tensile properties (3.5.3.1), hardness (3.5.3.2), and average grain size (3.5.3.4) after heat treatment of each lot of bars and forgings.

4.2.1.3 Tolerances (3.7) of bars.

4.2.2 Periodic Tests

The following requirements are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.2.2.1 Fracture toughness (3.5.3.3) of bars and forgings after heat treatment.

4.2.2.2 Ability of forging stock (3.5.4) to develop required properties.

4.2.2.3 Frequency-severity cleanliness rating (3.6.1).

4.2.2.4 Grain flow of die forgings (3.6.3).

4.3 Sampling and Testing

4.3.1 Bars and Forging Stock

In accordance with AMS2370.